

**WICANDERS START SPC**

Technical Data Sheet	Standard	Unit	Value
Dimension (LxWxT)	-	mm	1225x190x5,2
Mass per unit	-	Kgs / m2	9,4
Packaging (box / pallet)	-	M2	1,629 / 71,676
Level of use Domestic	ISO 10874	Class	23
Level of use Commercial	ISO 10874	Class	31

**General properties - EN 16511**

Thickness, t -	ISO 24337	$\Delta t_{avg} \leq 0,50$ mm, relative to nominal value / $t_{max} - t_{min} \leq 0,50$ mm	Complies
Length, l	ISO 24337	$\leq 1\ 500$ mm: $\Delta l \leq 0,5$ mm / $> 1\ 500$ mm: $\Delta l \leq 0,3$ mm/m	Complies
Width, w	ISO 24337	$\Delta w_{avg} \leq 0,10$ mm, relative to nominal value / $w_{max} - w_{min} \leq 0,20$ mm	Complies
Squareness, q	ISO 24337	$max \leq 0,20$ mm	Complies
Straightness, s	ISO 24337	$max \leq 0,30$ mm/m	Complies
Openings, o	ISO 24337	$max \leq 0,20$ mm	Complies
Height difference, h	ISO 24337	$h_{max} \leq 0,15$ mm	Complies
Flatness of the panel (Length - concave / convex)	ISO 24337	concave $\leq 0,50$ %, / convex $\leq 1,0$ %	Complies
Flatness of the panel (Width - concave / convex)	ISO 24337	concave $\leq 0,15$ %, / convex $\leq 0,20$ %	Complies

**Classification properties - EN 16511**

Wear resistance IP	EN 15468, procedure B	$\geq 1\ 500$ cycles	Complies
Impact resistance [mm] (big ball)	EN 13329:2006+A1:2008, Annex F	$\geq 800$ mm	Complies
Castor chair resistance	EN 425	25 000 cycles	Complies
Resistance to staining	EN 438-2	Groups 1 and 2: grade 4 Group 3: grade 3	Complies
Residual Indentation	EN ISO 24343-1	$\leq 0,3$ mm	Complies
Swelling	ISO 24336	$\leq 20$ %	Complies

**Safety properties - EN 14041**

Fire resistance	EN ISO 11925-2 + EN ISO 9239-1 : Class EN 13501-1	Class	Cfl-s1
Slip Classification	EN 13893	Class	DS
Formaldehyde emission	EN 717-1	Class	E1
Content pentachlorophenol (PCP)	EN 14041 Annex B	mg/kg	Undetectable

**Additional properties**

Impact sound reduction	EN ISO 10140	dB ( $\Delta L_w$ )	tests on going
Walking noise	IHD-W431	dB %	tests on going
Thermal resistance (Thermal conductivity)	EN ISO 10456	m2·K/W	tests on going

**ASTM Standards**

Residual indentation	ASTM F1914	avg . 0.007 in. (0.18 mm)	Complies
Static load limit	ASTM F970 / F387	max loading: 250 lb/in.2 (1.72 MPa) max residual indent: 0.005 in. (0.13 mm)	Complies
Squareness	ASTM F2055	max 0.010 in. (0.25 mm)	Complies
Dimensional Stability	ASTM F2199 / ISO 23999	0.2 % / lineal ft (305 mm) max	Complies
Thickness (with back layer)	ASTM F387	as specified $\pm 0.008$ in. (0.20 mm) min 0.080 in. (2.0 mm)	Complies
Airborne sound transmission loss	ASTM E90 /ASTM E413	STC (dB)	tests on going
Impact sound transmission	ASTM E492 /ASTM E989	IIC (dB)	tests on going
Impact sound transmission	ASTM E2179	$\Delta IIC$	tests on going